



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08K 3/24, 3/38	A1	(11) International Publication Number: WO 92/02578 (43) International Publication Date: 20 February 1992 (20.02.92)
<p>(21) International Application Number: PCT/GB91/01280</p> <p>(22) International Filing Date: 29 July 1991 (29.07.91)</p> <p>(30) Priority data: 9016555.6 27 July 1990 (27.07.90) GB</p> <p>(71) Applicant (for all designated States except US): ALCAN INTERNATIONAL LIMITED [CA/CA]; 1188 Sherbrooke Street West, Montreal, Quebec H3A 3G2 (CA).</p> <p>(72) Inventor; and (75) Inventor/Applicant (for US only) : CHAPLIN, Dominic [GB/GB]; 15 Dale Court, Seymour Road, Slough, Berkshire SL1 2NU (GB).</p> <p>(74) Agents: LIGHTFOOT, Robert, O. et al.; Raworth, Moss & Cook, 36 Sydenham Road, Croydon, Surrey CR0 2EF (GB).</p>		<p>(81) Designated States: AT, AT (European patent), AU, BB, BE (European patent), BF (OAPI patent), BG, BJ (OAPI patent), BR, CA, CF (OAPI patent), CG (OAPI patent), CH, CH (European patent), CI (OAPI patent), CM (OAPI patent), DE, DE (European patent), DK, DK (European patent), ES, ES (European patent), FI, FR (European patent), GA (OAPI patent), GB, GB (European patent), GN (OAPI patent), GR (European patent), HU, IT (European patent), JP, KP, KR, LK, LU, LU (European patent), MC, MG, ML (OAPI patent), MR (OAPI patent), MW, NL, NL (European patent), NO, PL, RO, SD, SE, SE (European patent), SN (OAPI + patent), SU, TD (OAPI patent), TG (OAPI patent), US.</p> <p>Published <i>With international search report.</i></p>
<p>(54) Title: FIRE-RETARDANT COMPOSITIONS</p> <p>(57) Abstract</p> <p>This invention relates to fire-retardant polymer compositions, and preferably, but not exclusively, to fire-retardant polyamide compositions. It has now been found that the combination of a zinc borate and a divalent metal stannate, particularly zinc stannate, in halogen-containing polymeric compositions provides an increased fire-retardant effect, which is greater than that expected from the use of either zinc borate or the stannate alone. The combination also suppresses smoke production. Preferably the stannate is zinc stannate.</p>		

+ See back of page

+ DESIGNATIONS OF "SU"

It is not yet known for which States of the former Soviet Union any designation of the Soviet Union has effect.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MN	Mongolia
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GN	Guinea	NL	Netherlands
BJ	Benin	GR	Greece	NO	Norway
BR	Brazil	HU	Hungary	PL	Poland
CA	Canada	IT	Italy	RO	Romania
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU ⁺	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
DE	Germany	MC	Monaco	US	United States of America
DK	Denmark				

-1-

Fire-Retardant Compositions

5 This invention relates to fire-retardant polymer compositions, and preferably, but not exclusively, to fire-retardant polyamide compositions. It will be understood by those in the art that the term "fire-retardant" encompasses "flame-retardant".

10 The use of zinc borate or zinc stannate as components of fire-retardant compositions is well known in the art. The use of zinc borate is described in U.S. Patent No. 4360616 and U.S. Patent No. 4504611.

15 U.S. Patent No. 4360616 describes a glass-reinforced flame-retardant polyamide composition having good arc tracking resistance and consisting of:

- 20 a) 40-65 weight percent of a polyamide of film-forming molecular weight,
- b) 16-35 weight percent of melamine, melam, melamine cyanurate or a melamine derivative,
- 25 c) 1-7 weight percent selected from the group consisting of a chlorinated compound obtained from the condensation of two moles of perchloro-cyclopentadiene and one mole of 1,5-cyclooctadiene, or a brominated polystyrene,
- 30 d) 1-4.9 weight percent of zinc borate or zinc oxide, and
- e) 5-30 weight percent of glass fibres.

SUBSTITUTE SHEET

-2-

U.S. Patent No. 4,504,611 similarly describes a flame-retardant polyamide consisting, in percent by weight, of:

- 5 a) 35-76% polyamide,
- b) 6-10% zinc borate,
- c) 10-15% melamine cyanurate,
- d) 0-35% fibreglass,
- e) 0-3% antimony trioxide, and
- 10 f) 8-15% of a chlorinated compound.

Although there is disclosure of the use of a zinc borate with zinc oxide, there is no reference in this prior art to the use of zinc stannate.

15

It has now been found that the combination of a zinc borate and a divalent metal stannate, particularly zinc stannate, in halogen-containing polymeric compositions provides an increased fire-retardant effect, which is greater than that expected from the use of either zinc borate or the stannate alone. The combination also suppresses smoke production. Where the term "stannate" is used herein in a general sense it includes "hydroxy stannate" in view of their similar fire-retardant properties.

25

According to the present invention, there is provided a fire-retardant polymer composition comprising a polymer and a fire-retardant amount of a mixture of a zinc borate and a divalent metal stannate, wherein the composition includes a source of halogen.

30

The source of halogen can be the polymer itself or can be a separate component, such as an organic

SUBSTITUTE SHEET

-3-

halogen-containing fire-retardant, provided that the component is compatible with the polymer.

5

Preferably the fire-retardant compositions of the present invention comprise, by weight percent:

- a) 40-94% polyamide,
- 10 b) 5-40% halogen-containing organic fire retardant,
- c) 1-20% of a mixture of zinc borate and a divalent metal stannate in a weight percentage ratio of between 10:90 and 90:10, more preferably of the order of 50:50.

15

Examples of suitable stannates that can be used are zinc stannate, zinc hydroxystannate, calcium hydroxystannate and magnesium hydroxystannate. Preferably the stannate is zinc stannate.

20

The constitution of zinc borate is variable as is described in the paper entitled "Applications of zinc borate in polymer blends and alloys" by W.J. Kennelly in the report of the Proceedings of the Fire Retardant Chemicals Association meeting held at Hilton Head Island, South Carolina, March 17th to 20th 1991 pages 199 to 205.

25

Whilst any zinc borate can be used, that of the formula $2\text{ZnO}_2 \cdot 3\text{B}_2\text{O}_3 \cdot 3.5\text{H}_2\text{O}$ - known as "ZB 2335" - is preferred and is the borate that is intended in this specification unless indicated to the contrary.

30

Examples of suitable polymers include polyesters, epoxy resins, ABS combinations and the like, but preferably, a polyamide is used. Halogenated polymers such a PVC can also be used in this invention and since they act as a

SUBSTITUTE SHEET

-4-

source of halogen no separate halogen-containing component is needed.

5 Polyamides are thermoplastic compounds, constructed of the bifunctional monomers, dicarboxylic acid and diamine, the properties of which are related to the length of the hydrocarbon radicals. One general class of polyamides used in the present invention is "nylon".

10 One example of nylon is polyhexamethylene adipamide (Nylon 66) formed by condensing hexamethylene diamine and adipic acid. Other examples include polyhexamethylene azelaamide (Nylon 69), polyhexamethylene sebacamide (Nylon 610), polylauric lactam, polycaprolactam (Nylon
15 6), poly-11-aminoundecanoic acid and poly-bis-(4-aminocyclohexyl) methane dodecanoamide.

The organic halogen-containing fire-retardant used can be any of those known in the art, such as those described in
20 U.S.-A-4,360,616 and U.S.-A-4,504,611, particularly that sold under the trade mark Dechlorane. Other examples include poly-dibromo-phenylene oxide, decabromo-diphenyl oxide and octabromo-diphenyl oxide.

25 A zinc borate and a divalent metal stannate added together, preferably in a weight ratio of 50:50, to the composition results in an unexpected synergistic fire-retardant effect, i.e. increase in the fire-retardant properties of the compositions beyond that
30 expected.

The inclusion of both a zinc borate and a divalent metal stannate in the fire-retardant composition also has the

SUBSTITUTE SHEET

-5-

result that antimony compounds are not required. This is extremely useful as these compounds are expensive, relatively hazardous and promote smoke when burning.

5 One or more conventional fire-retardants such as zinc oxide and tin oxide can be used in addition to the combination of a zinc borate and a divalent metal stannate, if desired.

10 The composition may also include other known additives such as glass fibre, calcium carbonate, talc or clay.

The present invention will now be described by way of the following Examples.

15

Example 1

In order to test the fire-retardant characteristics of the present invention, the following tests were performed
20 on sample test strips.

A UL94 test developed by the U.S. Underwriters Laboratory involves the use of a test strip 12 mm wide. The thickness of the strip can vary but is stated in each
25 test.

The strip is held vertically and the flame of a Bunsen burner applied for 10 seconds before being removed. After the strip is extinguished the Bunsen flame is
30 applied for a further 10 seconds and then removed. The total burning time after the two applications is measured.

SUBSTITUTE SHEET

-5-

The whole procedure is then repeated for verification.

Results from the various tests are then evaluated and classified as either V-0 (the best), V-1, V-2 or fail. For thermoplastics a V-0 pass for a 1.5 mm strip thickness is considered to be a good pass.

The second test used in evaluating the fire-retardant properties of the compositions is the COI test. This involves limiting the oxygen concentration in an oxygen nitrogen mixture to that which will just sustain combustion. The test strip is here again held vertically and the flame applied to the top of the strip.

A number of test strips were prepared according to normal practice from Nylon 66 using three different loadings of fire-retardant. The chlorine-containing fire-retardant Declorane was also present. The compositions of the three formulations are set out in Table 1 and are expressed as weight percentages of the total composition. Three thicknesses of test strip were used, namely 3, 1.5 and 0.75 mm, and the fire-retardant used was also varied so that zinc borate alone, zinc stannate alone and the combination of both zinc borate and zinc stannate were tested.

The results of the UL94 and COI tests on the test strips are set out in Tables 2, 3 and 4.

From the Tables it can be seen that when zinc borate and zinc stannate are used together in a weight ratio of 50:50 the fire-retardant properties are synergistically increased.

SUBSTITUTE SHEET

-7-

For Formulation 1 with a fire retardant loading of 10% by weight, zinc borate alone gave a value of V-0 in the UL94 test for the 3 mm and 1.5 mm thickness specimens. The thinnest specimen, however, gave a value of V-1. Zinc stannate alone on the other hand gave a value of V-0 for all three thicknesses. The combination of zinc borate and zinc stannate also gave a value of V-0 for all three thicknesses.

10 The results for Formulation 2 - a 7.5% by weight fire-retardant loading - again show a trend to an unexpected increase in fire-retardant properties using the combination of the two zinc compounds.

15 Formulation 3 with a 5% by weight fire retardant loading again showed an increased effect with the combination of zinc borate and zinc stannate. Zinc stannate alone gave a value of V-1 for all three test thicknesses and in combination with zinc borate also gave a value of V-0 for all three samples.

Example 1

25 A series of six samples based on polyvinylchloride were prepared having the basic composition as set out in Table 5 and including a total of 10 phr of zinc fire-retardant but in which the relative amounts of zinc borate and zinc stannate were varied between 0 and 100%.

30 Each sample was flame tested and the COI amounts of smoke and carbon monoxide (CO) measured. The smoke test followed BS 6401:1983 using wire mesh-supported 0.8 mm specimens, whilst the CO concentration was measured

SUBSTITUTE SHEET

-6-

after 2 minutes after insertion of the sample into the flame test.

5 The results are presented in Table 6 and show that better fire-retardant properties were obtained from the samples containing both zinc borate and zinc stannate than would have been expected for the relative proportion used.

10 As well as resulting in a synergistic fire-retardant effect the present invention also allows for the use of a decreased amount of zinc borate and zinc stannate relative to the amount used when either component is used on its own.

15 It should also be noted that antimony trioxide is not required in the present invention, thus eliminating potential toxic waste posed by the use of this compound.

20

25

30

SUBSTITUTE SHEET



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08K 3/24, 3/38	A1	(11) International Publication Number: WO 92/02578 (43) International Publication Date: 20 February 1992 (20.02.92)
(21) International Application Number: PCT/GB91/01280 (22) International Filing Date: 29 July 1991 (29.07.91) (30) Priority data: 9016555.6 27 July 1990 (27.07.90) GB (71) Applicant (for all designated States except US): ALCAN INTERNATIONAL LIMITED [CA/CA]; 1188 Sherbrooke Street West, Montreal, Quebec H3A 3G2 (CA). (72) Inventor; and (75) Inventor/Applicant (for US only) : CHAPLIN, Dominic [GB/GB]; 15 Dale Court, Seymour Road, Slough, Berkshire SL1 2NU (GB). (74) Agents: LIGHTFOOT, Robert, O. et al.; Raworth, Moss & Cook, 36 Sydenham Road, Croydon, Surrey CR0 2EF (GB).		(81) Designated States: AT, AT (European patent), AU, BB, BE (European patent), BF (OAPI patent), BG, BJ (OAPI patent), BR, CA, CF (OAPI patent), CG (OAPI patent), CH, CH (European patent), CI (OAPI patent), CM (OAPI patent), DE, DE (European patent), DK, DK (European patent), ES, ES (European patent), FI, FR (European patent), GA (OAPI patent), GB, GB (European patent), GN (OAPI patent), GR (European patent), HU, IT (European patent), JP, KP, KR, LK, LU, LU (European patent), MC, MG, ML (OAPI patent), MR (OAPI patent), MW, NL, NL (European patent), NO, PL, RO, SD, SE, SE (European patent), SN (OAPI + patent), SU, TD (OAPI patent), TG (OAPI patent), US. Published <i>With international search report.</i>
(54) Title: FIRE-RETARDANT COMPOSITIONS (57) Abstract This invention relates to fire-retardant polymer compositions, and preferably, but not exclusively, to fire-retardant polyamide compositions. It has now been found that the combination of a zinc borate and a divalent metal stannate, particularly zinc stannate, in halogen-containing polymeric compositions provides an increased fire-retardant effect, which is greater than that expected from the use of either zinc borate or the stannate alone. The combination also suppresses smoke production. Preferably the stannate is zinc stannate.		

+ See back of page

+ DESIGNATIONS OF "SU"

It is not yet known for which States of the former Soviet Union any designation of the Soviet Union has effect.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MN	Mongolia
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GN	Guinea	NL	Netherlands
BJ	Benin	GR	Greece	NO	Norway
BR	Brazil	HU	Hungary	PL	Poland
CA	Canada	IT	Italy	RO	Romania
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland			SN	Senegal
CI	Côte d'Ivoire	KR	Republic of Korea	SU ⁺	Soviet Union
CM	Cameroon	LI	Liechtenstein	TD	Chad
CS	Czechoslovakia	LK	Sri Lanka	TG	Togo
DE	Germany	LU	Luxembourg	US	United States of America
DK	Denmark	MC	Monaco		

-1-

Fire-Retardant Compositions

5 This invention relates to fire-retardant polymer compositions, and preferably, but not exclusively, to fire-retardant polyamide compositions. It will be understood by those in the art that the term "fire-retardant" encompasses "flame-retardant".

10 The use of zinc borate or zinc stannate as components of fire-retardant compositions is well known in the art. The use of zinc borate is described in U.S. Patent No. 4360616 and U.S. Patent No. 4504611.

15 U.S. Patent No. 4360616 describes a glass-reinforced flame-retardant polyamide composition having good arc tracking resistance and consisting of:

- 20 a) 40-65 weight percent of a polyamide of film-forming molecular weight,
- b) 16-35 weight percent of melamine, melam, melamine cyanurate or a melamine derivative,
- 25 c) 1-7 weight percent selected from the group consisting of a chlorinated compound obtained from the condensation of two moles of perchloro-cyclopentadiene and one mole of 1,5-cyclooctadiene, or a brominated polystyrene,
- 30 d) 1-4.9 weight percent of zinc borate or zinc oxide, and
- e) 5-30 weight percent of glass fibres.

SUBSTITUTE SHEET

-2-

U.S. Patent No. 4,504,611 similarly describes a flame-retardant polyamide consisting, in percent by weight, of:

- 5 a) 35-76% polyamide,
- b) 6-10% zinc borate,
- c) 10-15% melamine cyanurate,
- d) 0-35% fibreglass,
- e) 0-3% antimony trioxide, and
- 10 f) 8-15% of a chlorinated compound.

Although there is disclosure of the use of a zinc borate with zinc oxide, there is no reference in this prior art to the use of zinc stannate.

15

It has now been found that the combination of a zinc borate and a divalent metal stannate, particularly zinc stannate, in halogen-containing polymeric compositions provides an increased fire-retardant effect, which is greater than that expected from the use of either zinc borate or the stannate alone. The combination also suppresses smoke production. Where the term "stannate" is used herein in a general sense it includes "hydroxy stannate" in view of their similar fire-retardant properties.

25

According to the present invention, there is provided a fire-retardant polymer composition comprising a polymer and a fire-retardant amount of a mixture of a zinc borate and a divalent metal stannate, wherein the composition includes a source of halogen.

30

The source of halogen can be the polymer itself or can be a separate component, such as an organic

SUBSTITUTE SHEET

-3-

halogen-containing fire-retardant, provided that the component is compatible with the polymer.

5

Preferably the fire-retardant compositions of the present invention comprise, by weight percent:

10

- a) 40-94% polyamide,
- b) 5-40% halogen-containing organic fire retardant,
- c) 1-20% of a mixture of zinc borate and a divalent metal stannate in a weight percentage ratio of between 10:90 and 90:10, more preferably of the order of 50:50.

15

Examples of suitable stannates that can be used are zinc stannate, zinc hydroxystannate, calcium hydroxystannate and magnesium hydroxystannate. Preferably the stannate is zinc stannate.

20

The constitution of zinc borate is variable as is described in the paper entitled "Applications of zinc borate in polymer blends and alloys" by W.J. Kennelly in the report of the Proceedings of the Fire Retardant Chemicals Association meeting held at Hilton Head Island, South Carolina, March 17th to 20th 1991 pages 199 to 205.

25

Whilst any zinc borate can be used, that of the formula $2ZnO_2 \cdot 3B_2O_3 \cdot 3.5H_2O$ - known as "ZB 2335" - is preferred and is the borate that is intended in this specification unless indicated to the contrary.

30

Examples of suitable polymers include polyesters, epoxy resins, ABS combinations and the like, but preferably, a polyamide is used. Halogenated polymers such as PVC can also be used in this invention and since they act as a

SUBSTITUTE SHEET

-4-

source of halogen no separate halogen-containing component is needed.

5 Polyamides are thermoplastic compounds, constructed of the bifunctional monomers, dicarboxylic acid and diamine, the properties of which are related to the length of the hydrocarbon radicals. One general class of polyamides used in the present invention is "nylon".

10 One example of nylon is polyhexamethylene adipamide (Nylon 66) formed by condensing hexamethylene diamine and adipic acid. Other examples include polyhexamethylene azelaamide (Nylon 69), polyhexamethylene sebacamide (Nylon 610), polylauric lactam, polycaprolactam (Nylon
15 6), poly-11-aminoundecanoic acid and poly-bis-(4-aminocyclohexyl) methane dodecanoamide.

The organic halogen-containing fire-retardant used can be any of those known in the art, such as those described in
20 U.S.-A-4,360,616 and U.S.-A-4,504,611, particularly that sold under the trade mark Dechlorane. Other examples include poly-dibromo-phenylene oxide, decabromo-diphenyl oxide and octabromo-diphenyl oxide.

25 A zinc borate and a divalent metal stannate added together, preferably in a weight ratio of 50:50, to the composition results in an unexpected synergistic fire-retardant effect, i.e. increase in the fire-retardant properties of the compositions beyond that
30 expected.

The inclusion of both a zinc borate and a divalent metal stannate in the fire-retardant composition also has the

SUBSTITUTE SHEET

-5-

result that antimony compounds are not required. This is extremely useful as these compounds are expensive, relatively hazardous and promote smoke when burning.

5 One or more conventional fire-retardants such as zinc oxide and tin oxide can be used in addition to the combination of a zinc borate and a divalent metal stannate, if desired.

10 The composition may also include other known additives such as glass fibre, calcium carbonate, talc or clay.

The present invention will now be described by way of the following Examples.

15

Example 1

In order to test the fire-retardant characteristics of the present invention, the following tests were performed
20 on sample test strips.

A UL94 test developed by the U.S. Underwriters Laboratory involves the use of a test strip 12 mm wide. The thickness of the strip can vary but is stated in each
25 test.

The strip is held vertically and the flame of a Bunsen burner applied for 10 seconds before being removed. After the strip is extinguished the Bunsen flame is
30 applied for a further 10 seconds and then removed. The total burning time after the two applications is measured.

SUBSTITUTE SHEET

-5-

The whole procedure is then repeated for verification.

Results from the various tests are then evaluated and classified as either V-0 (the best), V-1, V-2 or fail. For thermoplastics a V-0 pass for a 1.5 mm strip thickness is considered to be a good pass.

The second test used in evaluating the fire-retardant properties of the compositions is the COI test. This involves limiting the oxygen concentration in an oxygen-nitrogen mixture to that which will just sustain combustion. The test strip is here again held vertically and the flame applied to the top of the strip.

A number of test strips were prepared according to normal practice from Nylon 66 using three different loadings of fire-retardant. The chlorine-containing fire-retardant Declorane was also present. The compositions of the three formulations are set out in Table 1 and are expressed as weight percentages of the total composition. Three thicknesses of test strip were used, namely 3, 1.5 and 0.75 mm, and the fire-retardant used was also varied so that zinc borate alone, zinc stannate alone and the combination of both zinc borate and zinc stannate were tested.

The results of the UL94 and COI tests on the test strips are set out in Tables 2, 3 and 4.

From the Tables it can be seen that when zinc borate and zinc stannate are used together in a weight ratio of 50:50 the fire-retardant properties are synergistically increased.

SUBSTITUTE SHEET

-7-

- For Formulation 1 with a fire retardant loading of 10% by weight, zinc borate alone gave a value of V-0 in the UL94 test for the 3 mm and 1.5 mm thickness specimens. The thinnest specimen, however, gave a value of V-1. Zinc stannate alone on the other hand gave a value of V-0 for all three thicknesses. The combination of zinc borate and zinc stannate also gave a value of V-0 for all three thicknesses.
- 10 The results for Formulation 2 - a 7.5% by weight fire-retardant loading - again show a trend to an unexpected increase in fire-retardant properties using the combination of the two zinc compounds.
- 15 Formulation 3 with a 5% by weight fire retardant loading again showed an increased effect with the combination of zinc borate and zinc stannate. Zinc stannate alone gave a value of V-1 for all three test thicknesses and in combination with zinc borate also gave a value of V-0 for all three samples.
- 20

Example 1

- 25 A series of six samples based on polyvinylchloride were prepared having the basic composition as set out in Table 5 and including a total of 10 phr of zinc fire-retardant but in which the relative amounts of zinc borate and zinc stannate were varied between 0 and 100%.
- 30 Each sample was flame tested and the COI amounts of smoke and carbon monoxide (CO) measured. The smoke test followed BS 401:1982 using wire mesh-supported 0.8 mm specimens, whilst the CO concentration was measured

SUBSTITUTE SHEET

-6-

after 2 minutes after insertion of the sample into the flame test.

5 The results are presented in Table 6 and show that better fire-retardant properties were obtained from the samples containing both zinc borate and zinc stannate than would have been expected for the relative proportion used.

10 As well as resulting in a synergistic fire-retardant effect the present invention also allows for the use of a decreased amount of zinc borate and zinc stannate relative to the amount used when either component is used on its own.

15 It should also be noted that antimony trioxide is not required in the present invention, thus eliminating potential toxic waste posed by the use of this compound.

20

25

30

SUBSTITUTE SHEET

TABLE 1

		Weight		
5		Formulation	Formulation	Formulation
		1	2	3
	Nylon 66	70	77.5	85
	Dechlorane	20	15	10
10	Zinc Fire Retardant	10	7.5	5
	Total	100	100	100

15

TABLE 2

20

ZINC FIRE RETARDANT Formulation

25

TEST	ZINC BORATE		ZINC STANNATE		ZINC BORATE ZINC STANNATE	
					50 50	
UL-94 3 mm	0-0		0-0		0-0	
UL-94 1.5 mm	0-0		0-0		0-0	
UL-94 0.75mm	0-1		0-0		0-1	
30 COI	20		12		19	

SUBSTITUTE SHEET

-10-

TABLE 3

ZINC FIRE RETARDANT (Formulation 2)

5

TEST	ZINC BORATE	ZINC STANNATE	ZINC BORATE/ ZINC STANNATE
			50:50
10	UL-94 3 mm	V-0	V-0
	UL-94 1.5 mm	V-1	V-0
	UL-94 0.75mm	V-1	V-1
	COI	29	30

15

TABLE 4

20

ZINC FIRE RETARDANT (Formulation 3)

TEST	ZINC BORATE	ZINC STANNATE	ZINC BORATE/ ZINC STANNATE
			50:50
25	UL-94 3 mm	V-2	V-1
	UL-94 1.5 mm	V-2	V-1
	UL-94 0.75mm	V-2	V-1
	COI	28	28

30

SUBSTITUTE SHEET

-11-

TABLE 5

	Amount (phr)	Component	Product Name	Manufacturer
5	100	PVC	VY 110/51	Hydro Polymers
	50	DOP	Reomol	Ciba Geigy
	4	Stabiliser	Irgastab BC26	Ciba Geigy
10	0.7	Wax	Irgawax 371	Ciba Geigy

15

TABLE 6

	Sample	Amount of Zinc borate (phr)	Amount of Zinc stannate (phr)	COI	Smoke (D _m)	CO (ppm)
20	1	10	-	24.7	386	548
25	2	8	2	26.3	374	661
	3	6	4	26.6	365	720
	4	4	6	28.3	378	780
	5	2	8	28.5	355	820
	6	-	10	28.8	391	857
30						

SUBSTITUTE SHEET

Example 3

Eight samples of Nylon 66 were prepared and tested for their fire-retardant properties and their strength. The composition of these samples and the results are given in Table 7.

It can be seen that a substantial proportion of the expensive zinc stannate can be replaced by the cheaper zinc borate with no loss of fire-retardant performance, even though zinc borate on its own exhibited a very poor fire-retardant effect.

Example 4

It is known that Nylon 6 is more difficult to render fire-retardant than Nylon 66, partially due to its lower melting point of 220°C, as compared with 260°C for Nylon 66. A number of samples of Nylon 6 were prepared, all of which included 15% by weight of the halogen-containing fire-retardant Dechlorane. Various levels of zinc stannate were tested for strength and in accordance with UL-94, along with combinations with zinc borate. The results are given in Table 8, together with those for formulations containing tin and zinc oxides for comparison. All of the samples were conditioned at 23°C and a relative humidity of 50% for seven days before testing.

It can be seen that relatively high levels of additives are required to reach UL-94 V-0 at 0.8 mm or less, but that the combination of zinc stannate and zinc borate demonstrates an improved result.

SUBSTITUTE SHEET

-13-

Example 5

A number of different stannates were tested with rigid PVC using samples having the composition:-

5

100 phr PVC Hydro Polymers VY110, 51
 2 phr Calcium stearate
 2 phr TI7M, Tin stabilizer, Ciba Geigy
 5 phr Flame Retardant (as specified).

10

300 g batches of the samples were made up by compounding at 150°C in a two roll mill, and their COI's were measured using samples compression moulded to 2 mm and cut into 1 cm thick strips. The results are as follows:-

15

<u>Fire Retardant</u>	<u>COI</u>
Zinc hydroxystannate	67.5
Calcium hydroxystannate	57.5
20 Magnesium hydroxystannate	60.5
Zinc borate ZB2335	55.5
Zinc borate ZB223	57.0
25 Zinc Hydroxystannate/ZB2335	66.6 (5.0)
Calcium hydroxystannate/ZB2335	64.6 (8.2)
Magnesium hydroxystannate/ZB2335	66.4 (8.4)
Zinc hydroxystannate/ZB2335	66.6 (5.0)
30 Zinc hydroxystannate ZB223	72.4 (5.5)

ZB223 is a borate of the formula $2ZnO_2 \cdot B_2O_3 \cdot 3H_2O$.

SUBSTITUTE SHEET

-14-

All of the blends are 50-50 by weight, and the figures in brackets are the amounts by which the blends' COI's are greater than would be predicted by simple averaging of the two components.

5

The results show that the two zinc borates are effective fire retardants and give the same synergistic effect with zinc stannate, and that calcium and magnesium hydroxystannates also give a synergistic effect that is if anything larger than that of the zinc compound.

10

Magnesium hydroxystannate performed better in the tests as a smoke suppressant for rigid PVC than the other stannates tested.

15

20

25

30

SUBSTITUTE SHEET

-15-

TABLE 7

5

FORMULATION - WEIGHT %

	Nylon 66	100	77.5	80	80	82	82	82	82
	Dechlorane	-	15	15	15	12	12	12	12
10	Zinc Stannate	-	7.5	5	3	6	4	2	-
	ZB2235	-	-	-	2	-	2	4	6
	CL-94								
15	3.0 mm	V-2	V-O	V-O	V-O	V-O	V-O	V-O	V-O
	1.5 mm	V-2	V-O	V-O	V-O	V-O	V-O	V-O	Fail
	0.75 mm	V-2	V-O	V-O	V-O	V-1	V-1	V-O	Fail
	Notched Izod	135	69	88	83	84	91	83	-
20	Impact Strength (J/m)								
	Tensile Strength (N/mm ²)	70	66	74	73	71	73	72	-

25

Materials

	Nylon 66 A25	-	BIP
30	Dechlorane Pus 25	-	Occidental Chemical Corp.

SUBSTITUTE SHEET

TABLE 8

	UL-94 Rating			Tensile Strength -2 N/mm	Notched Izod Impact Strength J/M
	3mm	1.5mm	0.75mm		
7% Zinc stannate	V-0	V-1	Fail	58	110
6% Zinc stannate	V-0	Fail	Fail	58	114
5% Zinc stannate	V-1	Fail	Fail	58	112
4% Zinc stannate	Fail	Fail	Fail	58	123
1% Zinc stannate + 2% Zinc borate	V-0	V-0	V-1	57	127
3% Zinc stannate + 3% Zinc borate	V-0	Fail	Fail	56	124
2% Zinc stannate + 4% Zinc borate	V-1	Fail	Fail	57	127
6% Zinc borate	Fail	Fail	Fail	57	119
6% SnO ₂	V-0	V-1	Fail	57	122
4% SnO ₂ + 2% ZnO	Fail	Fail	Fail	56	150
6% ZnO	Fail	Fail	Fail	55	133
6% Sb ₂ O ₃	Fail	Fail	Fail	56	116
Unfilled Nylon 6	Fail	Fail	Fail	65	267

SUBSTITUTE SHEET

-17-

CLAIMS:


1. A fire-retardant polymer composition comprising a polymer and a fire-retardant amount of a mixture of a zinc borate and a divalent metal stannate, wherein the composition includes a source of halogen.
2. A composition as claimed in claim 1 wherein the stannate is zinc stannate.
3. A composition as claimed in claim 1 or claim 2 wherein the source of halogen is the polymer itself.
4. A composition as claimed in claim 3 wherein the polymer is polyvinylchloride.
5. A composition as claimed in claim 1 or claim 2 wherein the source of halogen is an organic halogen-containing fire-retardant which is compatible with the polymer.
6. A composition as claimed in claim 5 wherein the polymer is a polyamide.
7. A composition as claimed in claim 6 containing from 40 to 94% by weight of polyamide, from 5 to 40% by weight of a halogen-containing organic fire-retardant which is compatible with the polyamide, and from 1 to 20% by weight of a mixture of zinc borate and zinc stannate.
8. A composition as claimed in any one of the preceding claims wherein the zinc borate and the stannate are present in the composition in approximately the same amounts by weight.

SUBSTITUTE SHEET

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 91/01280

I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. 5 C08K3/24; C08K3/38		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.Cl. 5	C08K	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claims No. ¹³
X	WORLD PATENTS INDEX LATEST Derwent Publications Ltd., London, GB; AN 82-50923E & JP,A,57 076 042 (KANEGAFUCHI CHEM KK) 12 May 1982 see abstract	1-2,5,8
A	FR,A,2 341 619 (IMPERIAL CHEMICAL INDUSTRIES) 16 September 1977 see claims 1,10	1,5-6
<p>¹⁰ Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is considered with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"A" document member of the same patent family</p>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
06 NOVEMBER 1991	13. 11. 91	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE	SIEMENS T. 	

Form PCT/ISA/210 (second sheet) (January 1985)

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO. GB 9101280
SA 49984**

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 06/11/91

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
FR-A-2341619	16-09-77	GB-A-	1572497	30-07-80
		AT-B-	356898	27-05-80
		AU-B-	507925	06-02-80
		AU-A-	2192877	10-08-78
		BE-A-	851665	22-08-77
		CA-A-	1090031	18-11-80
		CH-A-	626904	15-12-81
		DE-A, C	2706827	01-09-77
		JP-C-	1397633	07-09-87
		JP-A-	52102364	27-08-77
		JP-B-	61058496	11-12-86
		NL-A-	7701565	23-08-77
		SE-B-	432108	19-03-84
		SE-A-	7701605	21-08-77
		US-A-	4105621	08-08-78
<hr/>				

EPO FORM P047

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82